

Technical Data Sheet of SIS YH-4019

Product Name: Styrene Isoprene Styrene Block Copolymer (SIS)

Grade: SIS YH-4019

Structure: Radial

SIS YH-4019 Technical Data:

Items	Index
Form	White Fluffy Particle
SM Content, %	19
Volatile Matter, wt %	≤0.7
SI Content, %	30
Tensile Strength, Mpa	12
Hardness, Shore A	45
Melt Flow Rate (200°C ,5kg), g/10 min	10
Toluene Solution Viscosity (25 °C, 25%), Mpa.s	350
Note	FDA177.1810, FDA177.2600,Regulation (EC) No 1935/2004

Application

Pressure Sensitive Adhesive; Label Adhesive

Package

20kg PE bag 520/740kg super bag.

Storage

Store at room temperature (below 30°C), away from direct sunlight and UV radiation to prevent oxidative degradation of the isoprene middle block. The standard shelf life is 12 months from the date of manufacture.